



Solar Gard® Solar Control and Safety & Security Window Films

8 Mil Silver 35



Performance Results

4mm 4/12/4 mm

Visible Light

TR (%)	Transmittance	35	33
--------	---------------	----	----

Solar Energy

TR (%)	Transmittance	25	22
IR (%)	IR Rejection 780 to 2500 nm	86	-
UV (%)	UV blocked @300 to 380 nm	>99	>99
G	Solar Heat Gain Coefficient (G-value)	0,43	0,45
TSER (%)	Total Solar Energy Rejected	63	55
SHGR (%)	Solar Heat Gain Reduction	56	40
Tdw (%)	Fade Control UV Tdw-ISO @300 to 700 nm	28	26
FR (%)	Fade Reduction Factor	67	65

Physical Properties

Tnom/T(μm)	Thickness Nominal / Overall	200/250
TS- kg/cm ²	Tensile strength	2,11
ELONG	Elongation	>100%
PEEL-g/cm	Peel Strength	>985
YIELD-kg/cm ²	Yield Strength (at 5%)	21,6
BREAK-kg/cm	Break Strength	44
TEAR-kg	Tear Strength (Graves)	6
PUNC-kg	Puncture Strength	60

Safety Testing (For details on safety testing and test reports, consult www.solargard.com or contact your local authorized dealer/distributor.)

EN 12600	Human Impact	1B1
EN 356	Resistance to Manual Attack	Y
ISO 16933, GSA or ASTM	Bomb Blast Resistance	Y

